



MASTER CHEMICALS TECHNOLOGY

MC- DECK SEAL W.B

Elastic & Protective Coating of Bitumen emulsion

Description :

MC-Deck Seal W.B is one component water base bitumen base free from tar and phenol. Protects concrete, plastering, brickwork and iron against water, earth-dampness (underground), normal atmospheric and industrial influences .

Uses :

MC-Deck Seal W.B gives a protective coating above and below ground. It may be applied on iron steel, concrete, brickwork, plastering and timber.

MC-Deck Seal W.B is recommended for the protection of roofing felts.

Advantages:

MC- Deck Seal W.B gives glossy finish and after drying is odorless. The coating or film remains is resistant up to a temperature of 80 °C. It is ready-to-use, and if correctly applied, produces satisfactory results at an economical cost.

MC-Deck Seal W.B conforms to standards of ASTM D 1227-95 type III .

Technical Data:

Form	: High viscous liquied
Color	: Dark brown
Density	: $1.05 \pm 0.02 \text{ g/ cm}^3$
Consumption rate	: $4\text{-}5 \text{ m}^2 / \text{kg}$ (for concerte) : $4\text{-}6 \text{ m}^2 / \text{kg}$ (for metal)
Shelf life	: 18 months
Storage	: Away from sun light
Time of recoat	: 24hrs

Instruction for Use:

1-Before application of **MC-Deck Seal W.B** the surface to be protected should be thoroughly cleaned from dirt, loose particles and oily substances. Iron/steel should be free from rust . Application is carried out by brush or spray .

2-At least two coats of **MC-Deck Seal W.B** are recommended, but before application of the second coat it should be made quite certain that the prime or initial coating is thoroughly dry. Suggested waiting periods between first and second application, according to temperature, approx. 24 hours. Further additional coating naturally increase the protective capacity or resistance .

Packaging :

15 kg pails or 200 kg drum

*For More Technical details contact **Master Chemicals Technology** Technical Department.*

Or visit our website www.mc.com.eg

Master Chemicals Technology

11 Ahmed Kamal str, - Heliopolis

Tel / Fax : 26244491 / 26244492

Mob : 01001615868